


Helios 5



SPECIALISED WRAPPING

- ❑ HIGH QUALITY FILM
- ❑ RECOGNISED QUALITY
- ❑ 5 LAYER BLOW FILM
- ❑ SUITABLE FOR HIGH FLOW, 3D AND COMBI MACHINES
- ❑ HIGH STICKING POWER
- ❑ REINFORCED MECHANICAL PROPERTIES
- ❑ STRONG RESISTANCE TO RIPS AND PERFORATIONS
- ❑ HIGHER PLASTIC MEMORY
- ❑ UV PROTECTION FOR 12 MONTHS,
FOR A MAXIMUM OF 130 KLY (class A)



Special 3D | Combi




BLACK



WHITE



GREEN



Group
Barbier
Plastic solutions

Hélios[®]

5



Complies with NF EN14932
25μ



| | Values | | Test Method |
|---------------------|-----------------------|--------|-------------------------------|
| Width | 500 mm | 750 mm | ISO 4592 |
| Thickness | 25 microns | | ISO 4591 et ISO 4593 |
| Roll length | 1800 m | 1500 m | §9.4.EN14932 |
| Stress at break | SL>28 MPa / ST >23MPa | | EN ISO 527-1 EN ISO 527-3 |
| Elongation at break | SL>400% / ST >600% | | |
| DART TEST | 400 g | | EN ISO 7765-1: 2004 méthode A |
| Sealing | > 4 mBars | | Test BARBIER |

OUR FILM IS FREE OF HEAVY METALS

Our engagements

This commercial document has no contractual value. The information and photographs contained therein are not binding except the appreciated technical specifications in accordance with the EN14932 standard.

Only our F.I.C.C.U: Information Sheet, Tips and User Instructions (product catalogue) and / or our specifications (specific products) determines the content and the limits of our commitments regarding the technical features of our products.

Our F.I.C.C.U. (Information Sheet, Tips and User Instructions) can be obtained from your supplier.

You can also contact us via the email address: agricole@barbiergroup.com or on our website www.barbiergroup.com

Our recommandations

We recommend that before you order and use our films please:

- Read our Information Sheet, Tips and User Instructions.
- Discuss with your supplier our products for your specific operating conditions

Distributor Stamp

GRUPE BARBIER
LA GUIDE – BP 39
F 43602 SAINTE – SIGOLENE CEDEX
TELEPHONE : + 33.(0)4.71.75.11.11
FAX + 33.(0)4.71.66.15.01
Email : barbier@barbiergroup.com
Website : www.barbiergroup.com



Groupe
Barbier
Plastic solutions